

DATA SHEET

EPS TECHNICAL INFORMATION

What exactly is EPS?

EPS stands for Expanded Polystyrene. It is a lightweight cellular plastic material consisting of fine spherical shaped particles, which are comprised of 98% air. This is trapped within a number of closed hollow cells in each particle.

How is EPS manufactured?

When raw EPS particles containing a blowing or expanding agent are softened by heating with steam, the hollow closed cells are formed within the particles, which expand to up to 50 times their original volume. Blocks of EPS are made by resoftening the expanded particles in a block mould with steam until they fuse together. The block is then cut into sheets or boards. Shaped EPS products are produced either by cutting block with a hot wire or by direct moulding of the expanded particles in specially shaped moulds.

Does EPS absorb water?

EPS is a closed cell and cannot absorb water. During the process of moulding a block, tiny channels are formed between the particles. If the material is immersed in water these tiny channels can be filled with water. After immersion for more than 360 days, there may be up to 6% water content by volume which has entered the channels. Even under such an adverse and rare condition of prolonged saturation, EPS suffers little adverse effect. It maintains its shape, size, structure, cohesion and physical appearance.

The ability of EPS to resist the adverse effects of moisture is exemplified by its widespread use in floats, marinas and other applications which involve full or partial submergence in water for prolonged periods of time.

Is EPS durable?

Yes. Because EPS is an inert organic material, it will not rot and is highly resistant to mildew. It also provides no nutritive value to ants, termites and rodents.

To prevent damage to EPS by pests and insects seeking to gain access to the other materials in buildings which provide a food source, EPS may be coated with a thin cement slurry.

Does EPS contain CFC's?

No. EPS is chlorofluorocarbon (CFC) and hydrochlorofluorocarbon (HCFC) free.

Does EPS burn?

Because EPS boards contain a fire retardant additive, they do not present an undue fire hazard when correctly installed. Like timber, particle-board and other organic building materials, EPS will burn when in contact with a flame, due to the presence of the fire retardant additive, this flame will self extinguish almost immediately after the fire source is removed.

Does EPS give off toxic fumes?

The level of toxicity of EPS in a fire situation is no greater than that of timber and other commonly used building materials: the same toxic gas, carbon monoxide, is produced. Also produced are carbon dioxide and soot (carbon). There is no emission of such gases as hydrogen cyanide or hydrogen chloride.

DATA SHEET

EPS TECHNICAL INFORMATION

Physical Property	Unit	CLASS						Test Method
		"L"	"SL"	"S"	"M"	"H"	"VH"	
Nominal Densities of Rigid Cellular Polystyrene –guide only	kg/m ³	11	13.5	16	19	24	28	AS 1366.3
Compressive stress at 10 percent deformation (min)	kPA	50	70	85	105	135	165	AS 2498.3
Cross-breaking strength (min)	kPA	95	135	165	200	260	320	AS 2498.4
Rate of water vapour transmission (max.) measured parallel to rise at 23°C	µg/m ² s	710	630	580	520	460	400	AS2498.5
Dimensional stability of length, width, thickness (max.) at 70 °C, dry condition seven days	percent	1	1	1	1	1	1	AS 2498.6
Thermal resistance (min.) at a mean temperature of 25 °C	M ² .K/W	1	1.13	1.17	1.20	1.25	1.28	AS 2464.5 or AS 2464.6
Flame propagation characteristics: median flame duration (max.) eighth value (max.) median volume retained eighth value (min.)	s s percent percent	2 3 15 12	2 3 18 15	2 3 22 19	2 3 30 27	2 3 40 37	2 3 50 47	AS 2122.1

COMPARATIVE TESTING OF SOME MATERIALS TO AS 1530.3 - 1999

Material	Ignitability Index. (0-20)	Spread of Flame Index. (0-10)	Heat Evolved Index. (0-10)	Smoke Developed Index. (0-10)
EPS (I)	12	0	3	5
Softboard (ii)	16	9	7	3
Oregon (ii)	13	6	5	3
Blue Gum (ii)	11	0	3	2
Radiata Pine (iii)	14	8	9	3
Hardboard (iii)	14	7	9	5

Extensive research programs have been conducted overseas (iv) to determine if thermal decomposition products of EPS & XPS present a toxic hazard. The test results have revealed that these decomposition products are decidedly less harmful than those of burning wood and other conventional building materials. Gases released during combustion are predominantly carbon dioxide and, at much lower levels, carbon monoxide. A current CSIRO report (v) comments that the toxicity of the gases associated with the burning of EPS & XPS is no greater than that associated with timber.

- (i) AWTA – Test report no:9-96156.
- (ii) EBS Notes on science of building NSB-66.
- (iii) Australian Standard 1530.3 – 1999
- (iv) H.Hoffman and H.Oettal - Comparative toxicity of thermal decomposition products.
- (v) P.R Nicholl & K.G Martin – Toxicity considerations of combustion products from cellular plastics.

The information contained in this document is to the best of Printboard Industries knowledge true and accurate, but all instructions or suggestions are made without any guarantee. Since the conditions of use are beyond the control of Printboard Industries, Printboard Industries disclaims any liability for loss or damage suffered from the use of this data or suggestions. Furthermore no liability is accepted if the use of any product in accordance with the data or suggestions infringes any patent.